

Stein- und Mörtelverbrauch von Lehmsteine

Bezeichnung		Steinverbrauch/m ²			Mörtelverbrauch Nassmörtel Liter/pro m ²		
		Wandstärke			Wandstärke		
		11,5	24,0	17,5	11,5	24,0	17,5
DF	240x115x52	63 St.	126 St.		29	80	
NF	240x115x71	48 St.	96 St.		27	75	
2 DF	240x115x113	32 St.	64 St.		25	60	
3 DF	240x175x113		43 St.	32 St.		55	35
8 DF	498x115x238	8 St.			10	21	
12 DF	498x175x238			8 St.			20